

COLOUR INDEX AND PROPERTIES

| PETROMATE | | C.I. No. | Spe.Gr. @20°C | Xylene insolubles | Moisture % | Viscosity Cst. @25°C | Flash Point °C |
|-----------|---|-----------------------|------------------|----------------------|---------------|-------------------------|-------------------|
| Yellow 07 |  | Solvent Yellow 107 | 0.99 | 0.50 | 0.30 | <120 | 28-35 |
| Yellow 14 |  | Solvent Yellow 124 | 0.98 | 0.20 | 0.30 | <100 | 65 |
| Orange R |  | Proprietary | 1.01 | 0.15 | 0.30 | <100 | 28-35 |
| Orange 11 |  | Proprietary | 0.95 | 0.15 | 0.30 | <15 | 28-35 |
| Orange 16 |  | Solvent Orange 98 | 0.98 | 0.20 | 0.30 | <15 | 28-35 |
| Red 11 |  | Solvent Red19 | 1.02 | 0.20 | 0.20 | <25 | 65 |
| Red 13* |  | Solvent Red164 | 1.02 | 0.30 | 0.32 | <80 | 28-35 |
| Red 1309* |  | Solvent Red164 | 1.01 | 0.30 | 0.30 | <15 | 28-35 |
| Red 04 |  | Proprietary | 1.02 | 0.25 | 0.30 | <100 | 28-35 |
| Purple 16 |  | Proprietary | 1.01 | 0.30 | 0.30 | <15 | 28-35 |
| Purple 24 |  | Proprietary | 1.01 | 0.30 | 0.25 | <15 | 28-35 |
| Blue HF |  | Proprietary | 0.98 | 0.60 | 0.35 | <15 | 65-72 |
| Blue 16 |  | Solvent Blue 98 | 0.98 | 0.48 | 0.30 | <15 | 28-35 |
| Blue 02 |  | Solvent Blue 98 | 0.99 | 0.20 | 0.30 | <15 | 28-35 |
| Blue 14HF |  | Solvent Blue 79 | 0.92 | 0.25** | 0.25 | <15 | 65 |
| Green 12 |  | Solvent Green 33 | 0.99 | 0.20 | 0.30 | <70 | 28-35 |
| Green 03 |  | Proprietary | 0.96 | 0.30 | 0.40 | <15 | 28-35 |
| Green 02 |  | Proprietary | 0.96 | 0.30 | 0.30 | <15 | 28-35 |
| Green 07 |  | Proprietary | 0.98 | 0.25 | 0.30 | <15 | 28-35 |
| Green 10 |  | Proprietary | 0.98 | 0.25 | 0.30 | <15 | 28-35 |
| Bronze 10 |  | Proprietary | 0.99 | 0.20 | 0.40 | <15 | 28-35 |
| Brown 17 |  | Proprietary | 1.00 | 0.40 | 0.40 | <15 | 28-35 |
| Black 04 |  | Proprietary | 0.96 | 0.25 | 0.25 | <15 | 28-35 |

*These products can also be made available in heavier aromatic solvents where a high flash point is required. ** Toluene insolubles